

Belgian Textile Association

**· B · T · A · SR, S.r.o.**

Budovateľská 38, 080 01 Prešov

## Technical file quality 1008

09/03/2012

|                                          |                                         |                                  |
|------------------------------------------|-----------------------------------------|----------------------------------|
| <b>Quality</b>                           | <b>: 100% polyester /tricot lining/</b> |                                  |
| <b>Width</b>                             | <b>: 158 cm ± 3%</b>                    | <b>methode: ISO 22198:2006</b>   |
| <b>Weight</b>                            | <b>: 100 gr/m2 ± 3%</b>                 | <b>methode: ISO 3801 - 1977</b>  |
| <b>Shrinkage 60°C</b> =                  | <b>: - 0,5 %</b>                        |                                  |
| <b>Shrinkage 60°C</b>                    | <b>: ± 0 %</b>                          |                                  |
| <b>Colorfastness to washing at 60°C:</b> |                                         | <b>methode: ISO 105-C06:2010</b> |
| - staining in PES                        | <b>: 4/5-5</b>                          |                                  |
| - staining in cotton                     | <b>: 4/5-5</b>                          |                                  |
| - colorchange                            | <b>: 4/5-5</b>                          |                                  |
| <b>Colorfastness to rubbing:</b>         |                                         |                                  |
| <b>Rubbing dry</b>                       | <b>: 4/5-5</b>                          |                                  |
| <b>Rubbing wet</b>                       | <b>: 4/5</b>                            |                                  |
| <b>Care instruction:</b>                 |                                         |                                  |



**Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.**

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293