

Belgian Textile Association

· B · T · A · SR, s.r.o.

B u d o v a t e ľ s k á 38, 080 01 P r e š o v

Technical file quality 1024

02/02/2004

Quality : 100% polyester

Width : 147 cm +/- 3% methode: ISO 22198:2006

Weight : 235 gr/m2 +/- 3% methode: ISO 3801 - 1977

Shrinkage Warp / Weft 30°C : -0,5 % / -0,5 %

Tear force methode: ELMENDORF ISO 13937 – 1: 2000

- the warp yarns tear at : 6,4 [kg]

- the weft yarns tear at : 6,4 [kg]

Breaking load methode: ISO 13934-1:1999

- the warp yarns tear at : 95 [kg]

- the weft yarns tear at : 85 [kg]

Colorfastness to washing at 30°C: methode: ISO 105-C06:2010

	light shades	dark shades
- staining in PES	: 4/5-5	4
- staining in cotton	: 4	3-3/4
- colorchange	: 4/5-5	4/5-5

Colorfastness to rubbing:

Rubbing dry : 4/5-5 4-5

Rubbing wet : 4/5-5 4-5

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293