

Belgian Textile Association

· B · T · A · SR, S.R.O.

Budovateľská 38, 080 01 Prešov

Technical file quality 1027

17/07/2012

| | | |
|--|---|--|
| Quality | : 74% polyester + 19% VI +7% spandex | |
| Width | : 150 cm +/- 3% | methode: ISO 22198:2006 |
| Weight | : 210 gr/m2 +/- 3% | methode: ISO 3801 - 1977 |
| Shrinkage Warp / Weft 30°C | : -0,5 % / 0 % | |
| Shrinkage Warp / Weft 60°C | : - 1 % / 0 % | |
| Tear force | | methode: ELMENDORF ISO 13937 – 1:2000 |
| - the warp yarns tear at | : 4,5 | [kg] |
| - the weft yarns tear at | : 3,3 | [kg] |
| Breaking load | | methode: 13934-4:1999 |
| - the warp yarns tear at | : 84 | [kg] |
| - the weft yarns tear at | : 70 | [kg] |
| Colorfastness to washing at 30°C: | | methode: ISO 105-C06:2010 |
| | light shades | dark shades |
| - staining in PES | : 4/5-5 | 3/4 |
| - staining in cotton | : 4/5-5 | 3/4 |
| - colorchange | : 4/5-5 | 4/5-5 |
| Colorfastness to rubbing: | | |
| Rubbing dry | : 4/5-5 | 4/5 |
| Rubbing wet | : 4/5-5 | 3 |
| Care instruction: | | |



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293