

Belgian Textile Association

· B · T · A · SR, s.r.o.

B u d o v a t e ľ s k á 38, 080 01 P r e š o v

Technical file quality 1031

04/07/2005

Quality : 30% PAD + 67% VI + 3% spandex

Width : 147 cm +/- 3% **methode:** ISO 22198:2006

Weight : 235 gr/m2 +/- 3% **methode:** ISO 3801 - 1977

Shrinkage Warp / Weft 30°C : -1 % / -3 %

Tear force **methode:** ELMENDORF ISO 13937 – 1:2000

- the warp yarns tear at : 2,5 [kg]

- the weft yarns tear at : 3 [kg]

Colorfastness to washing at 30°C: **methode:** ISO 105-C06:2010

	light shades	dark shades
- staining in PES	: 4/5-5	3
- staining in cotton	: 4/5	3-3/4
- colorchange	: 4/5-5	4/5-5

Colorfastness to rubbing:

Rubbing dry : 4/5-5 **4**

Rubbing wet : 4/5 **3**

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293