

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Technical file quality 1072

12/02/2004

Quality : 97% cotton + 3% elastan

Width : 140 cm +/- 3% methode: ISO 3832 – 1976

Weight : 350 gr/m² +/- 3% methode: ISO 3801 - 1976

Shrinkage Warp / Weft 30°C : -1 % / -1 %

Tear force

methode: ELMENDORF ISO 13937 - 1

- the warp yarns tear at : 1,8 [kg]

- the weft yarns tear at : 1,3 [kg]

Breaking load

methode: ISO 5081

- the warp yarns tear at : 47 [kg]

- the weft yarns tear at : 22 [kg]

Colorfastness to washing at 30°C:

methode: ISO 105-C06:1994

	light shades	dark shades
- staining in PES	: 4/5-5	4/5-5
- staining in cotton	: 4/5-5	4/5-5
- colorchange	: 4/5-5	4/5-5

Colorfastness to rubbing:

Rubbing dry : 4/5-5 3-3/4

Rubbing wet : 4-5 3

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293