

Technical file quality 1075
25/08/2003

Quality : 100% cotton

Width : 150 cm +/- 3% methode: ISO 3832 – 1976

Weight : 285 gr/m2 +/- 3% methode: ISO 3801 - 1976

Shrinkage Warp / Weft 30°C : -4 % / +4 %

Tear force methode: ELMENDORF ISO 13937 - 1

- the warp yarns tear at : 2,6 [kg]

- the weft yarns tear at : 1,2 [kg]

Breaking load

methode: ISO 5081

- the warp yarns tear at : 58 [kg]

- the weft yarns tear at : 17 [kg]

Colorfastness to washing at 30°C:

methode: ISO 105-C06:1994

	light shades	dark shades
- staining in PES	: 4-5	4
- staining in cotton	: 4-5	3/4
- colorchange	: min. 3/4	min. 3/4

Colorfastness to rubbing:

Rubbing dry	: 4-5	3
Rubbing wet	: 3-5	2-3

Care instruction:



Attention: Produkt wash before first used.

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.