

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Technical file quality 1520

02/02/2005

Quality	: 100% cotton		
Width	: 150 cm +/- 3%		methode: ISO 22198:2006
Weight	: 240 gr/m2 +/- 3%		methode: ISO 3801 - 1977
Shrinkage Warp / Weft 30°C	: -2 % / -1 %		
Tear force			methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2,2	[kg]	
- the weft yarns tear at	: 2,4	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 84	[kg]	
- the weft yarns tear at	: 63	[kg]	
Colorfastness to washing at 30°C:			methode: ISO 105-C06:2010
	light shades		dark shades
- staining in PES	: 4/5-5		4/5
- staining in cotton	: 4/5-5		4/5
- colorchange	: 4/5-5		4/5
Colorfastness to rubbing:			
Rubbing dry	: 4/5-5		3/ 4 -4
Rubbing wet	: 4/5-5		3-4
Care instruction:			



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293