

Technical file quality 1526 Sky Flex
10/04/2006

Quality : 98% cotton+ 2% elastan

Width : 155 cm +/- 3% methode: ISO 3832 – 1976

Weight : 255 gr/m2 +/- 3% methode: ISO 3801 - 1976

Shrinkage Warp / Weft 30°C : +0,5% / +0,5 %

Tear force methode: ELMENDORF ISO 13937 - 1

- the warp yarns tear at : 2,5 [kg]

- the weft yarns tear at : 1,6 [kg]

Breaking load methode: ISO 5081

- the warp yarns tear at : 93 [kg]

- the weft yarns tear at : 30 [kg]

Colorfastness to washing at 30°C: methode: ISO 105-C06:1994

- staining in PES : 4/5-5

- staining in cotton : 4/5-5

- colorchange : 4/5-5

Colorfastness to rubbing:

Rubbing dry : 4/5-5

Rubbing wet : 4/5-5

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.