

Belgian Textile Association

· B · T · A · SR, S.R.O.

Budovateľská 38, 080 01 Prešov

Technical file quality 1903

20/12/2004

Quality	: 100% polyester, hydrophobe treatment	
Width	: 154 cm +/- 3%	methode: ISO 22198:2006
Weight	: 56,5 gr/m2 +/- 3%	methode: ISO 3801 - 1977
Density per cm	: 39 x 32	
Shrinkage Warp / Weft 30°C	: 0 % / 0 %	
Tear force		methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2	[kg]
- the weft yarns tear at	: 2,3	[kg]
Breaking load		methode: ISO 13934-1:1999
- the warp yarns tear at	: 75	[kg]
- the weft yarns tear at	: 77	[kg]
Colorfastness to washing at 30°C:		methode: ISO 105-C06:2010
- staining in PES	: 4-5	
- staining in cotton	: 4-5	
- colorchange	: 4-5	
Colorfastness to rubbing:		
Rubbing dry	: 4-5	
Rubbing wet	: 4-5	
Spray test	: 100	methode: ISO 4920:1981
Care instruction:		



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293