

Belgian Textile Association

· B · T · A · SR, S.R.O.

Budovateľská 38, 080 01 Prešov

Technical file quality 1908 herringbone

13/10/2005

Quality	: 100% polyester		
Width	: 150 cm +/- 3%		methode: ISO 22198:2006
Weight	: 60 gr/m2 +/- 3%		methode: ISO 3801 – 1977
Density	: 41,3 x 29,9		
Shrinkage Warp / Weft 30°C	:- 0,5 % / - 0,5 %		
Tear force			methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2,2	[kg]	
- the weft yarns tear at	: 2,0	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 67	[kg]	
- the weft yarns tear at	: 55	[kg]	
Colorfastness to washing at 30°C:			methode: ISO 105-C06:2010
- staining in PES	: 4/5		
- staining in cotton	: 4/5-5		
- colorchange	: 4/5-5		
Colorfastness to rubbing:			
Rubbing dry	: 4		
Rubbing wet	: 4/5-5		

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293