

Belgian Textile Association

. B · T · A · SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Technical file quality 5065

17/07/2012

Quality : 100% polyester

Width : 160 cm +/- 3% methode: ISO 22198:2006

Weight : 82 g/m² +/- 3% methode: ISO 3801 - 1977

Shrinkage 30° and 40°C: warp/weft : -0,5% / -0,5%

Tear force

methode: ELMENDORF ISO 13937 – 1:2000

- the warp yarns tear at : 2,2 [kg]

- the weft yarns tear at : 2,8 [kg]

Breaking load

methode: ISO 13934-1:1999

- the warp yarns tear at : 65 [kg]

- the weft yarns tear at : 75 [kg]

Colorfastness to washing at 40°C:

methode: ISO 105-C06:2010

black

- staining in PES : 4/5-5

- staining in cotton : 4/5

- colorchange : 4/5-5

Colorfastness to rubbing:

Rubbing dry : 4/5

Rubbing wet : 4/5-5

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293