

Technical file quality 5545
01/04/2008

Quality : 55% cotton + 45% polyester

Width : 154 cm +/- 3% methode: ISO 22198:2006

Weight : 150 gr/m2 +/- 3% methode: ISO 3801 - 1977

Shrinkage Warp / Weft 30°C : -2 % / -2 %

Tear force methode: ELMENDORF ISO 13937 – 1:2000

- the warp yarns tear at : 1,9 [kg]

- the weft yarns tear at : 1,6 [kg]

Breaking load methode: ISO 13934-1:1999

- the warp yarns tear at : 80 [kg]

- the weft yarns tear at : 72 [kg]

Colorfastness to washing at 30°C: methode: ISO 105-C06:2010

- staining in PES : 4/5-5

- staining in cotton : 4/5-5

- colorchange : 4/5-5

Colorfastness to rubbing:

Rubbing dry : 2/3

Rubbing wet : 3

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293