

Belgian Textile Association

· B · T · A · SR, S.R.O.


Budovateľská 38, 080 01 Prešov

Technical file quality 5930 ivory

17/07/2012

Quality	: 50 % cotton + 50% polyester		
Width	: 168 cm +/- 3%		methode: ISO 22198:2006
Weight	: 118 gr/m2 +/- 3%		methode: ISO 3801 - 1977
Density per cm	: 25 x 23		
Shrinkage Warp / Weft 30°C	: -1,5% / -1,5 %		
Tear force			methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2,7	[kg]	
- the weft yarns tear at	: 2,4	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 65	[kg]	
- the weft yarns tear at	: 52	[kg]	

Care instruction:




Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293

Technical file quality 5930 black

17/07/2012

Quality	: 50 % cotton + 50% polyester		
Width	: 168 cm +/- 3%		methode: ISO 22198:2006
Weight	: 125 gr/m2 +/- 3%		methode: ISO 3801 - 1977
Density per cm	: 26 x 24		
Shrinkage Warp / Weft 30°C	: -1,5% / -1,5 %		
Tear force			methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2,7	[kg]	
- the weft yarns tear at	: 2,4	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 62	[kg]	
- the weft yarns tear at	: 60	[kg]	
Colorfastness to washing at 30°C:			methode: ISO 105-C06:2010
- staining in PES	: 4-4/5		
- staining in cotton	: 4/5		
- colorchange	: 4/5-5		
Colorfastness to rubbing:			
Rubbing dry	: 4-4/5		
Rubbing wet	: 3/4		
Care instruction:			



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.