

Technical file quality 5931 ecru

17/07/2012

Quality	: 23 % cotton + 77% polyester	
Width	: 170 cm +/- 3%	methode: ISO 22198:2006
Weight	: 147 gr/m2 +/- 3%	methode: ISO 3801 - 1977
Density per cm	: 31 x 23,4	
Shrinkage Warp / Weft 30°C	: -1% / -1 %	
Shrinkage Warp / Weft 40°C	: -1% / -1,5 %	
Shrinkage Warp / Weft 60°C	: -2% / -1,5 %	
Shrinkage Warp / Weft 90°C	: -3% / -2 %	
Shrinkage after ironing Warp / Weft 110°C	: -0,5% / 0 %	
Tear force	methode: ELMENDORF ISO 13937 – 1: 2000	
- the warp yarns tear at	: 3,8	[kg]
- the weft yarns tear at	: 4,3	[kg]
Breaking load	methode: ISO 13934-1:1999	
- the warp yarns tear at	: 95,3	[kg]
- the weft yarns tear at	: 71,1	[kg]
Colorfastness to washing at 60°C:	methode: ISO 105-C06:2010	
- staining in PES	: 4/5-5	
- staining in cotton	: 4/5-5	
- colorchange	: 4/5-5	

Colorfastness to rubbing:

Rubbing dry	: 4/5-5
Rubbing wet	: 4/5-5

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Belgian Textile Association

· B · T · A · SR, S.R.O.

Budovateľská 38, 080 01 Prešov

Technical file quality 5931 black

17/07/2012

Quality	: 23 % cotton + 77% polyester		
Width	: 156 cm +/- 3%		methode: ISO 22198:2006
Weight	: 170 gr/m2 +/- 3%		methode: ISO 3801 - 1977
Density per cm	: 31 x 28		
Shrinkage Warp / Weft 30°C	: -1% / -1 %		
Tear force			methode: ELMENDORF ISO 13937 – 1: 2000
- the warp yarns tear at	: 3	[kg]	
- the weft yarns tear at	: 2,5	[kg]	
Breaking load			methode: ISO 13934-1: 1999
- the warp yarns tear at	: 115	[kg]	
- the weft yarns tear at	: 90	[kg]	
Colorfastness to washing at 60°C:	methode: ISO 105-C06:2010		
- staining in PES	: 3/4		
- staining in cotton	: 3/4		
- colorchange	: 4/5-5		
Colorfastness to rubbing:			
Rubbing dry	: 4/5		
Rubbing wet	: 4-4/5		

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293

Technical file quality 5931 color

17/07/2012

Quality	: 35 % cotton + 65% polyester		
Width	: 156 cm +/- 3%		methode: ISO 22198:2006
Weight	: 168 gr/m2 +/- 3%		methode: ISO 3801 - 1977
Density per cm	: 32 x 26		
Shrinkage Warp / Weft 30°C	: -1% / -1 %		
Tear force			methode: ELMENDORF ISO 13937 – 1: 2000
- the warp yarns tear at	: 3,2	[kg]	
- the weft yarns tear at	: 3,7	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 105	[kg]	
- the weft yarns tear at	: 79	[kg]	
Colorfastness to washing at 60°C:	methode: ISO 105-C06:2010		
- staining in PES	: 4-4/5		
- staining in cotton	: 3-3/4		
- colorchange	: 4/5-5		
Colorfastness to rubbing:			
Rubbing dry	: 4/5		
Rubbing wet	: 3/ 4-4		

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.