

Belgian Textile Association

· **B · T · A · SR**, s.r.o.

Budovateľská 38, 080 01 Prešov

Technical file quality 5933 ecru

05/03/2012

Quality	: 25 % cotton + 75% polyester	
Width	: 165 cm +/- 3%	methode: ISO 22198:2006
Weight	: 110 gr/m ² +/- 3%	methode: ISO 3801 - 1977
Density per cm	: 38,9 x 25,6	
Shrinkage Warp / Weft 30°C	: -1% / -1 %	
Shrinkage Warp / Weft 40°C	: -2% / -1 %	
Shrinkage Warp / Weft 60°C	: -6% / -1%	
Shrinkage Warp / Weft 90°C	: -10% / -1,5 %	
Shrinkage after ironing Warp / Weft 110°C	: -1,5% / 0 %	
Tear force	methode: ELMENDORF ISO 13937 – 1:2000	
- the warp yarns tear at	: 2,2	[kg]
- the weft yarns tear at	: 3,9	[kg]
Breaking load	methode: ISO 13934-1:1999	
- the warp yarns tear at	: 62	[kg]
- the weft yarns tear at	: 72	[kg]

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293

Technical file quality 5933 colored

05/03/2012

Quality	: 25 % cotton + 75% polyester	
Width	: 165 cm +/- 3%	methode: ISO 322198:2006
Weight	: 130 gr/m2 +/- 3%	methode: ISO 3801 - 1977
Density per cm	: 41 x 29	
Shrinkage Warp / Weft 30°C	: -1% / -1 %	
Shrinkage Warp / Weft 60°C	: -2,5% / -1%	
Tear force		methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 1,2	[kg]
- the weft yarns tear at	: 2,4	[kg]
Breaking load		methode: ISO 13934-1:1999
- the warp yarns tear at	: 56	[kg]
the weft yarns tear at	: 92	[kg]
Colorfastness to washing at 40°C:		methode: ISO 105-C06:2010
- staining in PES	: 4-4/5	
- staining in cotton	: 4/5	
- colorchange	: 4/5-5	
Colorfastness to rubbing:		
Rubbing dry	: 4/5	
Rubbing wet	: 4/5	

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.