

Belgian Textile Association

**· B · T · A · SR, s.r.o.**

Budovateľská 38, 080 01 Prešov

## Technical file quality 5940

13/07/2012

**Quality** : 50 % cotton + 50% polyester

**Width** : 150 cm +/- 3% methode: ISO 22198: 2006

**Weight** black : 125 g/m<sup>2</sup> ± 3% methode: ISO 3801 - 1977  
ivory : 120 g/m<sup>2</sup> ± 3%

**Density per cm** : 24 x 23

**Shrinkage Warp / Weft 30°C** : -1,5 % / -1,5 %

**Tear force** methode: ELMENDORF ISO 13937 – 1:2000

- the warp yarns tear at : 1,8 [kg]

- the weft yarns tear at : 1,7 [kg]

**Breaking load** methode: ISO 13934-1:1999

- the warp yarns tear at : 55 [kg]

- the weft yarns tear at : 48 [kg]

**Colorfastness to washing at 30°C:** methode: ISO 105-C06: 2010

	ecru	black
- staining in PES	: 4/5-5	4/5
- staining in cotton	: 4/5-5	4/5
- colorchange	: 4/5-5	4/5-5

**Colorfastness to rubbing:**

**Rubbing dry** : 4/5-5 3/ 4-4

**Rubbing wet** : 4/5-5 3

**Care instruction:**



**Comments:** Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293