

Technical file quality 6150

11/04/2013

Quality	: 100% polyester + PU		
Width	: 155 cm +/- 3%	methode: ISO 22198:2006	
Weight	: 155 gr/m2 +/- 3%	methode: ISO 3801 - 1977	
Shrinkage Warp / Weft 40°C	: -1% / -1%		
Tear force		methode: ELMENDORF ISO 13937 – 1:2000	
- the warp yarns tear at	: 0,96	[kg]	
- the weft yarns tear at	: 0,96	[kg]	
Breaking load		methode: ISO 13934-1:1999	
- the warp yarns tear at	: 73	[kg]	
- the weft yarns tear at	: 32	[kg]	
Colorfastness to washing at 40°C:		methode: ISO 105-C06:2010	
- staining in PES	: 4/5		
- staining in cotton	: 4/5		
- colorchange	: 4/5-5		
Colorfastness to rubbing:			
Rubbing dry	: 4		
Rubbing wet	: 4		
Hydrostatic head /mm/	: > 2000	methode: ISO 811:1981	
after 5 washes at 40°C	: > 2000		
Spray test	: 100	methode: ISO 4920:2012	
Watervapour permeability			
Upright cup	: > 2000 / g/ m ² per 24hour /	methode: DIN 53122 clima B	
Inverse cup	: > 6000 / g/ m ² per 24hour /	methode: DIN 53122 clima B	

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.