

Technical file quality 6650
20/06/2006

Quality : 60% polyester+ 40% cotton

Width : 155 cm +/- 3% methode: ISO 3832 – 1976

Weight : 250 gr/m2 +/- 3% methode: ISO 3801 - 1976

Shrinkage Warp / Weft 30°C : -1% / -1 %
Shrinkage Warp / Weft 60°C : -2% / -2 %

Tear force methode: ELMENDORF ISO 13937 - 1
- the warp yarns tear at : 3,1 [kg]
- the weft yarns tear at : 3,3 [kg]

Breaking load methode: ISO 5081
- the warp yarns tear at : 105 [kg]
- the weft yarns tear at : 99 [kg]

Colorfastness to washing at 30°C: methode: ISO 105-C06:1994

	light shades	dark shades
- staining in PES	: 4-5	3/ 4-4
- staining in cotton	: 4-5	3-3/4
- colorchange	: 4-5	4/5

Colorfastness to washing at 60°C: methode: ISO 105-C06:1994

	light shades	dark shades
- staining in PES	: 4-5	3/4
- staining in cotton	: 4-5	3
- colorchange	: 4-5	4/5

Colorfastness to rubbing:

Rubbing dry	: 4-5	4-5
Rubbing wet	: 4-5	3-4

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Belgian Textile Association

• B • T • A • SR, s.r.o.

Budovateľská 38, 080 01 Prešov

Attention:Dark shades is not suitable combine with white.

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293