

Technical file quality 6652
20/06/2006

Quality : 60% polyester+ 40% cotton, with water-repelent treatment

Width : 155 cm +/- 3% methode: ISO 3832 – 1976

Weight : 250 gr/m2 +/- 3% methode: ISO 3801 - 1976

Shrinkage Warp / Weft 30°C : -1% / -1 %

Shrinkage Warp / Weft 60°C : -1% / -1 %

Tear force methode: ELMENDORF ISO 13937 - 1

- the warp yarns tear at : 3,1 [kg]

- the weft yarns tear at : 3,3 [kg]

Breaking load methode: ISO 5081

- the warp yarns tear at : 105 [kg]

- the weft yarns tear at : 99 [kg]

Colorfastness to washing at 30°C:

	light shades	dark shades
- staining in PES	: 4-5	3/ 4-4
- staining in cotton	: 4-5	3-3/4
- colorchange	: 4-5	4/5

methode: ISO 105-C06:1994

Colorfastness to washing at 60°C:

	light shades	dark shades
- staining in PES	: 4-5	3/4
- staining in cotton	: 4-5	3
- colorchange	: 4-5	4/5

methode: ISO 105-C06:1994

Colorfastness to rubbing:

Rubbing dry : 4-5 4-4/5

Rubbing wet : 4-5 3-4

Spray test : 80 methode: ISO 4920

Care instruction:



Attention: Dark shades is not suitable combine with white.

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.