

Technical file quality 6653
20/06/2006

Quality	: 60% polyester+ 40% cotton, fluoreflective colors, with water- repelent treatment			
Width	: 155 cm +/- 3%		methode: ISO 3832 – 1976	
Weight	: 235 gr/m2 +/- 3%		methode: ISO 3801 - 1976	
Shrinkage Warp / Weft 30°C	: -1,5% / -1,5 %			
Tear force			methode: ELMENDORF ISO 13937 - 1	
- the warp yarns tear at	: 3,3	[kg]		
- the weft yarns tear at	: 4,4	[kg]		
Breaking load			methode: ISO 5081	
- the warp yarns tear at	: 115	[kg]		
- the weft yarns tear at	: 92	[kg]		
Colorfastness to washing at 30°C:			methode: ISO 105-C06:1994	
- staining in PES	: 4			
- staining in cotton	: 3/ 4-4			
- colorchange	: 4/5-5			
Rubbing dry	: 4/5			
Rubbing wet	: 4/5			
Spray test	: 80		methode: ISO 4920	
Care instruction:				



Attention:This fabric is not suitable combine with white.

Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.