

Belgian Textile Association

· B · T · A · SR, s.r.o.

B u d o v a t e ľ s k á 38, 080 01 P r e š o v

Technical file quality 7002

17/07/2012

Quality	: 100% PAD + 2x PU	
Width	: 155 cm +/- 3%	methode: ISO 22198:2006
Weight	: 130 gr/m2 +/- 3%	methode: ISO 3801 - 1977
Density	: 27 x 19	
Shrinkage Warp / Weft 30°C	: -2% / -2 %	
Tear force		methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 2,9	[kg]
- the weft yarns tear at	: 2,1	[kg]
Breaking load		methode: ISO 1421:1998
- the warp yarns tear at	: 104	[kg]
- the weft yarns tear at	: 65	[kg]
Colorfastness to washing at 30°C:		methode: ISO 105-C06:2010
- staining in PAD	: 4-5	
- staining in cotton	: 4-5	
- colorchange	: 4-5	
Rubbing dry	: 4-5	
Rubbing wet	: 4-5	
Water column /mm/	: 2000	methode: ISO 811:1981
Spray test	:100	methode: ISO 4920:2012

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293