

Belgian Textile Association

**· B · T · A · SR, S.R.O.**

Budovateľská 38, 080 01 Prešov

## Technical file quality 7008

19/02/2008

<b>Quality</b>	<b>: 100% PAD, antistatic</b>		
<b>Width</b>	<b>: 152 cm +/- 3%</b>		<b>methode: ISO 22198:2006</b>
<b>Weight</b>	<b>: 60 gr/m2 +/- 3%</b>		<b>methode: ISO 3801 - 1977</b>
<b>Density per cm</b>	<b>: 42 x 31,5</b>		
<b>Shrinkage Warp / Weft 30°C</b>	<b>: -2% / -2,5%</b>		
<b>Tear force</b>			<b>methode: ELMENDORF ISO 13937 – 1:2000</b>
- the warp yarns tear at	<b>: 2,6</b>	<b>[kg]</b>	
- the weft yarns tear at	<b>: 2,2</b>	<b>[kg]</b>	
<b>Breaking load</b>			<b>methode: ISO 13934-1:1999</b>
- the warp yarns tear at	<b>: 56</b>	<b>[kg]</b>	
- the weft yarns tear at	<b>: 47</b>	<b>[kg]</b>	
<b>Colorfastness to washing at 30°C:</b>			<b>methode: ISO 105-C06:2010</b>
- staining in PAD	<b>: 4-5</b>		
- staining in cotton	<b>: 4-5</b>		
- colorchange	<b>: 4/5-5</b>		
<b>Rubbing dry</b>	<b>: 4/5-5</b>		
<b>Rubbing wet</b>	<b>: 4/5-5</b>		

**Care instruction:**



**Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.**

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293