

Belgian Textile Association

· B · T · A · SR, S.R.O.

Budovateľská 38, 080 01 Prešov

Technical file quality 7088

20/10/2006

Quality	: 100% PAD , hydrophobe treatment		
Width	: 152 cm +/- 3%		methode: ISO 22198:2006
Weight	: 60 gr/m2 +/- 3%		methode: ISO 3801 – 1977
Density	: 42 x 31,5		
Shrinkage Warp / Weft 30°C	: -1% / -2%		
Tear force			methode: ELMENDORF ISO 13937 – 1:2000
- the warp yarns tear at	: 3,8	[kg]	
- the weft yarns tear at	: 2,5	[kg]	
Breaking load			methode: ISO 13934-1:1999
- the warp yarns tear at	: 56	[kg]	
- the weft yarns tear at	: 47	[kg]	
Colorfastness to washing at 30°C:			methode: ISO 105-C06:2010
- staining in PAD	: 4-5		
- staining in cotton	: 4-5		
- colorchange	: 4/5-5		
Rubbing dry	: 4/5-5		
Rubbing wet	: 4/5-5		

Care instruction:



Comments: Above mentioned results are given for your guidance and are liable to undergo alterations.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293