

Belgian Textile Association

· B · T · A · SR, s.r.o.

B u d o v a t e l s k á 38, 080 01 P r e š o v

Technical file N2 P

16/04/2012

Product	: Seam sealing tape for 2-ply textiles	
Composition	: transparent polyurethane film on release paper	
Weight /film/	: 100 [g/m ²]	ISO 3801-5:2000
Width	: 20 or 22 [mm]	ISO 3932:2000
Film thickness	: 0,08 [mm]	ISO 9073-2
Softening/ Melting Kofler	: 130-160 [C°]	ISO 1218
Water column		ISO 811:2000
	new	: 5000 [mm]
	after 25 washes at 60°C	: 5000 [mm] (*)
	after 10 dry cleaning	: 5000 [mm] (*)

(*) depending on total weight of used fabric and type of coating

Recommended welding conditions on Pfaff machine

Roller pressure	: 1,0 bar
Air pressure	: 0,5 bar
Welding speed	: 26 %
Temperature set point	: 415°C
Roller composition	: upper roller: rubber : lower roller: steel

Certificates : ECO Label: Öko- Tex Standard 100
Centexbel test -No. 50103902

Comments: All data, suggestions and information supplied by or on behalf of Buddleia nv with respect to its products are based on research and deemed to be reliable. The values indicated in the TF describe typical properties but do not constitute specifications limits. However, since Buddleia has no influence on the use, processing and applications of the same, Buddleia can accept no responsibility whatsoever in this respect. The buyer shall check the quality and all other properties of the product and assumes all responsibilities arising from the use of the products and the information related thereto.

Tel.: 00421 (0) 51- 77 21 635, 6, 7 , Fax: 00421 (0) 51- 7724 293